

Data Sheet

EP2 GREASE

Spanjaard EP2 Grease is a high quality, all purpose, and lithium-based grease.

APPLICATIONS

Suitable for lubrication of plain, needle, ball and roller bearing of all types. **Spanjaard EP2 Grease** is fortified with rust and oxidation inhibitors.

Spanjaard EP2 Grease is suitable for lubrication of automotive, industrial equipment and mining equipment.

APPLICATION INSTRUCTIONS

Apply by hand or grease gun. Compatible with other competitive lithium greases. It is always a good practice to flush out old grease when switching lubricants. This is achieved by frequent re-greasing over a short time span.

It is essential that dust and dirt do not get into the bearings and care must be taken to prevent this during grease storage and packing of bearings.

HANDLING AND STORAGE

Store under cover with lid closed away from vibrating floor. Remove excess from skin and wash with Spanjaard Hand Cleaner followed by soap and water.

TYPICAL PROPERTIES

| Colour | Beige |
|---|-----------|
| Consistency - NLGI grade | 2 |
| Worked Penetration, 25°C, ¹ / ₁₀ mm | 280 |
| Thickener Lithiu | um Soap |
| Appearance Texture | Smooth |
| Drop Point, ⁰C | >180 |
| Dynamic Rust Test | <1 |
| Copper Corrosion - 24hr/100°C | Pass |
| Oil Separation 18h @ 40°C, % | <2 |
| Water Wash Out @ 38°C, % | <2 |
| @ 79°C, % | <4 |
| Rust Prevention | Pass |
| Timken OK Load, kg | >27 |
| Operating Temperature | |
| Continuous service, °C -2 | 20 to 120 |
| DASE OIL DRODEDTIES | |
| BASE OIL PROPERTIES Oil Viscosity cSt, 40°C | 200 |
| - | >225 |
| Flash Point, °C | >225 |
| | |



PACKAGING

400g cartridge; 500g; 5kg; 15kg; 50kg; 180kg.

CP/mg/ EP 2 Grease - Sep 2017

Certified as an ISO 9001 Manufacturer by the SABS

Manufacturers & Distributors of Special Lubricants & Allied Chemical Products SPANJAARD UK LIMITED 2 NEW STREET SQUARE LONDON EC4A 3BZ ENGLAND EMAIL: sales@spanjaard.bi SPANJAARD LIMITED PO BOX 7294 JOHANNESBURG 2000 SOUTH AFRICA TEL: +27 (0)11 386 7100 EMAIL: sales@spanjaard.b WEBSITE: www.spanjaard.b

电话: 021-58528856 59923197 传真: 021-58528166 E-mail: long@kunbond.com